

INNO-FIX FOX AQUAFUGA FX150

Cement Based, High-Performance, Water-Repellent Feature, Silicone Additive, Resistant to Mold and Dirt, Flex Joint Filler for Tiles and Ceramics

Description

FOX AQUAFUGA FX150, Cement based, water repellent, silicone added, resistant to mold and dirt formation; It is a flex joint filler that is used in the joints of materials such as tiles, ceramics, granites, natural stones and marbles and is not affected by temperature differences, water and vibration.

It meets the requirements of EN 13888-CG2WA.

CG: Cement Based Joint Filler

2: Enhanced additional features

W: Reduced Water Absorption

A: High Abrasion Resistance

Fields of Application

- Indoors and outdoors, horizontal and vertical applications
- Hotel, hospital, shopping mall, house etc.
- All wet areas
- It is appropriate to use in swimming pool and drinking water tanks.
- It can be used all kind of decorative applications.

Advantages

- It is resistant to mold and dirt due to its water repellent feature.
- Easy to clean.
- It is resistant to impacts, vibrations and detergents.
- It is resistant to freeze and thaw effect.
- It has high resistance to abrasions.
- It provides excellent adhesion without cracks at ceramic corners.
- Smooth surface is obtained.
- Easy to prepare and apply.
- Does not scratch glazed surfaces.
- Suitable for 2-8 mm joint gaps.
- It has long working time.
- Does not fade and change the color.

Technical Data

Structure of Material		Mineral fillers, Synthetic Additives, Special Polymers, Special Powder Silicones
Compressive Strength		>16 N/mm ²
Flexural Strength		>4 N/mm ²
Shrinkage Strength		<2 mm/m
Abrasion Strength		<1000 mm ³
Density		1,76 kg/lt
Water Absorption	30 minutes	<2 gr
	240 minutes	<5 gr
Application Surface Temperature		+5°C / +35°C
Service Temperature		-20°C / +80°C
Ripening Time		3-5 minutes
Usage Time		2 hours
Walkable Time		24 hours



The above values are given at +23°C and 50% relative humidity. High temperatures shorten the time, low temperatures lengthen the time.

Colors

1st Group Manhattan – Dark Grey- Cream – Light Cream– Bahama Beige- Light - Anemone - Champagne - Noche – Jasmin - Magnolia

2nd Group Black - Caramel - Tan - Powder – antique beige - Mittelbraun - Balıbraun – Bitter Brown- Chocolate - Cotto - Evergreen



www.foxbau.com

SARTECH YAPI MALZEMELERİ SANAYİ VE TİCARET LTD. ŞTİ.

Merkez: Organize Sanayi Bölgesi 1. Kısım 7. Cadde No:6 Döşemealtı/ANTALYA
Telefon: 0(242) 221 42 50 Fax: 0(242) 221 42 55
Şube : Yaytaş Mah. Organize Sanayi 7. Cadde No:21 Yenişehir/DIYARBAKIR
Web : www.foxbau.com E-mail : info@foxbau.com

Application Procedure

Substrate Preparation

Before starting the grouting application, it should be waited for the adhesive to gain sufficient strength. A waiting period of 48 hours is generally sufficient. The mortar residues in the joints should be cleaned and the joints should be emptied. Joints of highly absorbent materials must be moistened before filling.

Mixing

Clean water as described on the packaging is put into a clean mixing bowl. The **FOX AQUAFUGA FX150** bucket is opened and slowly added into the water, and mixed for about 4 minutes until it becomes homogeneous with a 400-600 rpm mixing drill. There should be no lumps in the material. After the material is rested for 30 seconds, it is mixed again for 1 minute and made ready for application. Different water ratios and different mixing methods can cause undesirable color differences.

Mixing Ratios

Approximately 6,40±0,20 liters of water should be used for 20 kg/bag of **FOX AQUAFUGA FX150**.

Approximately 1,60±0,05 liters of water should be used for 5 kg/bag of **FOX AQUAFUGA FX150**.

Approximately 320±10 ml of water should be used for 1 kg of **FOX AQUAFUGA FX150**.

Application

The mixed material is placed in the joints by making diagonal movements with a rubber trowel. In deep joints, the material should be expected to collapse first and then this process should be repeated. In extremely hot weather and absorbent surfaces, the joint material may suddenly lose its water and cause superficial cracks. Therefore, before application, the joints should be slightly moistened with a wet sponge. When the materials left to dry reach the hardness of resisting finger pressure, the surfaces are finalized with a wet sponge and the remaining material on the ceramic surface is cleaned.

Cleaning of Tools

Tools and equipment used after the application should be cleaned with water immediately. After **FOX AQUAFUGA FX150** hardens, it can only be mechanically cleaned from the surface.

Watch Points

- Using different amounts of mixing water during the application causes a change in joint colors. For this reason, applications should be made without changing the amount of water. Excessive use of water will weaken the material, which may lead to powder spills and cracks. Sawdust should not be used in surface cleaning.

Consumption

Consumption Table for Cement Based Joint Fillers (Depth: 8mm)

Ceramic sizes / Joint Spacing	2 mm	3 mm	4 mm	5 mm	6 mm	7 mm
10x10	550	800	1100	1350	1600	2100
10x20	400	650	850	1050	1250	1700
15x15	450	650	900	1000	1350	1800
15x20	300	500	650	800	1000	1300
20x20	300	450	600	750	900	1200
20x25	275	400	500	700	800	1100
20x30	250	375	500	600	750	1000
30x30	200	300	400	500	600	800

Consumption amounts are theoretical. Indicates the powder product consumption. Values are given in gr/m².

Package

5 kg polyethylene bags, 20 polyethylene reinforced kraft bags

Shelf Life

Shelf life is 12 months from the date of production when properly stored at room temperature, away from direct sunlight between +5°C and +30°C. Opened packages should be closed and consumed within 1 week.

Storage

It should be stored in its unopened original package, in a cool and dry environment, protected from frost. In short-term storage, maximum 3 pallets should be placed on top of each other and shipment should be made with a first-in, first-out system. In long-term storage, pallets should not be placed on top of each other.



Safety Precautions

It is dangerous to approach storage and application areas with fire. Storage and application areas should be ventilated. During the application, work clothes, protective gloves, glasses and masks in accordance with the occupational and worker health rules should be used. During storage and application, it should not be contacted with the skin and eyes, in case of contact, it should be washed with plenty of water and soap, and if swallowed, a doctor should be consulted immediately. Food and beverage materials should not be brought into the application areas. It should be stored out of the reach of children. For detailed information, the Material Safety Data Sheet should be consulted.

Disclaimer

The data contained in this technical document is based on our scientific and practical knowledge. SARTECH Yapi Malzemeleri San. ve Tic. Ltd. Sti. only responsible for the quality of the product. SARTECH Yapi Malzemeleri San. ve Tic. Ltd. Sti. cannot be held responsible. The responsibility for the correct application of our product lies with the user. Our company is only responsible for the quality of the product. This catalog overrides the information in the previous catalogue. Our company reserves the right to make changes in any information and content details in this catalogue. It is essential to check that the information in the catalog is up-to-date and valid. All rights reserved.



www.foxbau.com

SARTECH YAPI MALZEMELERİ SANAYİ VE TİCARET LTD. ŞTİ.

Merkez: Organize Sanayi Bölgesi 1. Kısım 7. Cadde No:6 Döşemealtı/ANTALYA
Telefon: 0(242) 221 42 50 Fax: 0(242) 221 42 55
Şube : Yaytaş Mah. Organize Sanayi 7. Cadde No:21 Yenişehir/DIYARBAKIR
Web : www.foxbau.com E-mail : info@foxbau.com