

INNO-FIX FOX CERAPLUS® FX112

Cement and Polymer-based, Reduced Slip, Long Working Time, High Adhesion, Flexible, Adhesive Mortar

Description

FOX CERAPLUS® FX112, Cement and polymer based, reduced slip, long working time, high adhesion performance, suitable for all kinds of climatic conditions, can be used indoors and outdoors, horizontally and vertically, long-lasting, flexible for ceramic, tile, porcelain ceramic, natural stone materials adhesive fee.

It meets the requirements of EN 12004-1:2017 C2TES1.

Public Works Pos. No: 04.01301-04.01304

C2: Cement Based, Additional Features Improved, High Performance

T: Reduced slip

E: Open Waiting Time Extended

S1: Flexible

Usage Areas

- Adhering tiles, ceramics, porcelain ceramics, natural stone materials to cement-based surfaces such as concrete, plaster, screed in indoor and outdoor horizontal and vertical applications,
- Adhering tiles, ceramics, porcelain ceramics, natural stone materials to gypsum-based surfaces in indoor, horizontal and vertical applications,
- Bonding tiles, ceramics, porcelain ceramics, natural stone materials on insulation in wet places such as bathrooms, balconies, kitchens,
- Bonding in swimming pools, Turkish baths, water tanks, bathrooms, industrial floors, cold storages,
- It is used for bonding ceramics on ceramics in exterior coatings of buildings, renovation and repair works.

Advantages

- It mixes only with water.
- It saves time and labor with its long working time.
- It does not slip in vertical applications.
- Provides fast and easy application.
- Provides application opportunity on gypsum surfaces.
- · Resistant to freeze-thaw cycle.
- It adapts to the ground stresses arising from temperature differences and is not affected.

Technical Data

Structure of Material Density		Special cement, mineral fillers, Polyme 1,76 kg/lt	r additive
Color		Gray, White	
Splice Strength	28 days	≥1,0 N/mm²	
Beginning		≥1,0 N/mm²	
After immersion in water		≥1,9 N/mm ²	
After aging with heat		≥1,0 N/mm ²	
After the Freeze-Thaw cycle		≥1,6 N/mm²	
Application Thickness		3-8 mm	
Application Surface Temperature		+5°C / +35°C	
Serviceability Temperature		-20°C / +80°C	< ₽
Ripening Time		3–5 minutes	K
Usage Time		2 hours	
Open Waiting Time		30 minutes	
Slip (mm)		None	
Walkability Time		After 24 hours	
Joint Application		After 24 hours	
Reaction class to Fire		A2	

The above values are given at +23°C and 50% relative humidity. High temperatures shorten the time, low temperatures lengthen the time.







Application Procedure

Surface Preparation

Cement Based Surfaces

The surfaces to be applied must be sound, free from all kinds of dust and dirt and must be in balance. The areas requiring repair should be repaired with INNO-CRETE series repair mortars at least 1 day before. If the surface temperature is above +25°C, the surface should be slightly moistened.

Other Surfaces

Before applying on gas concrete, gypsum plaster, particle board, gypsum board, lime plaster surfaces with high water absorbency, FOX PRIMERA® FL220 is diluted with 1/1 water as a primer and applied to the surface. Adhesion is done at least 8 hours after the primer is applied.

Mixina

The appropriate amount of water described on the packaging is poured into a clean mixing bowl. The FOX CERAPLUS® FX112 bag is opened and slowly added into the water, and mixed for 3-4 minutes until it becomes homogeneous with a 400 - 600 rpm mixing drill. There should be no lumps in the material. After the material is rested for 3 minutes, it is mixed again for 1 minute to make it ready for application.

Mixing Ratios

For 25 kg/1 bag of **FOX CERAPLUS® FX112 Gray**, approximately 7,50±0,25 liters of water should be used. For 25 kg/1 bag of **FOX CERAPLUS® FX112 White**, approximately 8,00±0,25 lt of water should be used.

Application

A 1mm thick FOX CERAPLUS® FX112 layer is applied to the application surface with the flat side of the trowel. FOX CERAPLUS FX112 is applied to the area large enough to be covered within 30 minutes, which is the open waiting time, with the toothed side of the trowel in one direction to obtain a uniform thickness. It is recommended to apply 1mm thick FOX CERAPLUS® FX112 to the back of each ceramic in order to cover the defects on the application surface when bonding ceramics of different thicknesses. When applying the ceramics to the surface, the coating materials are floated in the mortar to ensure that they are fully in contact with the adhesive mortar. The application is completed by leaving the recommended joint gap according to the appropriate ceramic size. **INNO-**FIX Series joint fillers should be used to fill the left joint gaps. Joint application can be started after approximately 24 hours.

Applicability Test

For the ceramic applicability test on the adhesive, the open waiting time should be checked. Fingers are pressed to the adhesive on the applied surface. If the adhesive gets on the finger, the application of gluing ceramics and tiles is continued. If the glue does not get on the finger, it means that the application time of the glue has passed. In this case, the adhesive should be scraped from the surface and new adhesive should be applied.

Cleaning of the Tools

Tools and equipment used after the application should be cleaned with water immediately. After FOX CERAPLUS® **FX112** hardens, it can only be mechanically cleaned from the surface.

Coverages varies between 4-6 kg/m² depending on the tooth thickness of the ceramic comb to be used.

Watch Points

- In FOX CERAPLUS® FX112 application, if the ambient and surface temperature is below +5°C or above +35°C, suitable temperatures should be expected. It should not be applied in extremely hot, rainy and very windy weather.
- It should be protected from sun, rain, wind and frost for the first 24 hours in outdoor applications.
- · Working and reaction times in ceramic adhesive mortars are affected by air temperature, humidity and floor temperatures.
- High temperatures accelerate hydration and the working time is shortened accordingly. Low temperatures slow down hydration, which prolongs working time. In order for the material to complete its curing, the floor temperature and ambient temperature to be applied must not fall below the minimum allowable temperature.

Package

25 kg polyethylene reinforced kraft bag

Shelf Life

Shelf life is 12 months from the date of production when properly stored at room temperature, away from direct sunlight between +5°C and +30°C. Opened packages should be closed and consumed within 1 week.







Storage

It should be stored in its unopened original package, in a cool and dry environment, protected from frost. In short-term storage, maximum 3 pallets should be placed on top of each other and shipment should be made with a first-in, first-out system. In long-term storage, pallets should not be placed on top of each other.

Safety Precautions

It is dangerous to approach storage and application areas with fire. Storage and application areas should be ventilated. During the application, work clothes, protective gloves, glasses and masks in accordance with the occupational and worker health rules should be used. During storage and application, it should not be contacted with the skin and eyes, in case of contact, it should be washed with plenty of soap and water. If swallowed, a doctor should be consulted immediately. Food and beverage materials should not be brought into the application areas. It should be stored out of the reach of children. For detailed information, the Material Safety Data Sheet should be consulted.

Disclaimer

The data contained in this technical document is based on our scientific and practical knowledge. SARTECH Yapı Malzemeleri San. ve Tic. Ltd. Şti. Only responsible for the quality of the product. SARTECH Yapı Malzemeleri San. ve Tic. Ltd. Şti. cannot be held responsible. The responsibility for the correct application of our product belongs to the user. Our company is only responsible for the quality of the product. This catalog overrides the information in the previous catalogue. Our company reserves the right to make changes in any information and content details in this catalogue. It is essential to check that the information in the catalog is up-to-date and valid. All rights reserved.



Page 3 / 3