

INNO-FLOOR FOX ALPHA-CİLA FF860

Press Concrete Protective Gloss Polish Material

Description

FOX ALPHA-CİLA FF860 is acrylic based, solvent based, transparent, protective coating material for concrete surfaces. It is a top coat coating that provides a long-lasting protection, dust-free, surface resistance and aesthetic appearance, penetrating into the surface of any surface with natural appearance, coloured acid (stain), precast protection or surface hardener treatment.

Fields of Application

- In the protection of concrete and other cement based surfaces in buildings and infrastructures,
- On floors and walls where bright appearance is desired,
- In order to increase the service life of concrete,
- Surface hardener applied surfaces,
- On screed concrete

Advantages

- Easy to apply and use.
- Resistant to oil and fuel residues.
- Provides protection against all kinds of weather effects and fungus formation on the surfaces..
- Prevents dusting, provides a harder surface.
- Extremely easy to clean, smooth surface is obtained.
- Provides resistance against abrasion.
- Penetrates deeply and gives a lively appearance.
- Resistant to Freeze – Thaw cycle and has UV resistant.
- Can be applied with brush, roller and spray machine.
- Water vapour permeable when applied on exterior surfaces.
- Water repellent.

Technical Features

Structure of the Material	Liquid Acrylic Resin
Density	0,97 kg/lt
Final Appeal	Transparent Gloss
Flash Point	+25°C
Drying Time	2 hours
Application Surface Temperature	+10°C / +30°C

The above values are given for + 23 ° C and 50% relative humidity. High temperatures shorten the time, low temperatures extend the time.

Surface Quality

Concrete substrates to be applied must have a strong and sufficient compressive strength (at least 25 N / mm²), tensile strength at least 1.5 N / mm², humidity should be maximum 4%, ground temperature minimum + 8°C. In addition, it should be noted that the dew point of the ground is above +3°C. The substrate must be clean, dry and free from all kinds of dirt, oil, grease, coating and surface curing materials etc.

Application Procedure

Substrate Preparation

Concrete substrates to be applied should be prepared in a way to obtain an open porous surface by removing cement grout by using abrasive equipment (Shot Blasting, milling, diamond polishing etc.). Weak concrete pieces should be removed from the surface, small gaps, holes should be made completely open. The resulting dust should be cleaned with the help of an industrial vacuum cleaner. **INNO-CRETE** repair mortars should be used for substrate repairs, filling gaps and smoothing the surface.

Application Conditions

- In applications where new concrete will be poured, concrete should be expected to complete at least 28 days of curing.
- Surface moisture content should be below 4%.
- There should be no rising humidity according to ASTM. (Polyethylene cover test).

- Relative air humidity should be 80% maximum.
- Pay attention to dew and condensation!
- Dew and water vapour condensation on the floor that has not been applied or newly coated will damage the coating. To prevent this, the floor temperature must be above + 3°C.

Watch Points in Application;

Surface Temperature ; Minimum +10°C - Maximum +30°C
Ambient Temperature ; Minimum +10°C - Maximum +30°C
Material Temperature ; Minimum +10°C - Maximum +30°C

Mixing

FOX ALPHA-CİLA FF860, is a one component, ready to use product.

Application

FOX ALPHA-CİLA FF860 is applied in layers with brush, roll or a spray pump resistant to solvents. Application between coats should be done after 2-3 hours according to the ambient temperature. In order to get ideal performance from the product, a minimum of 2 coats should be applied. The layers should be increased according to the surface absorbency.

Cleaning of the Tools

After the application, the tools and equipment should be cleaned with solvent.

Coverage

0,20-0,30 Lt / m² (for 2 layers)

Watch Points

- While applying **FOX ALPHA-CILA FF860**, it should always be ensured that there is good ventilation, and it should be paid attention to wearing glasses, mask and gloves during application.
- It is recommended to apply **FOX ALPHA-CILA FF860** by spraying on the concrete surface to obtain a uniform structure. Since the material contains solvent, it is flammable. Necessary measures must be taken in storage and application. Care should be taken to ventilate the application areas thoroughly, not to smoke in the environment, and to avoid electrical short circuits.
- No water should be added into FOX ALPHA-CILA FF860.

Package

5 lt Tin Gallon
17 lt Tin Gallon
200 lt Barrel

Shelf Life

It is 12 months from the production date under suitable storage conditions. Opened packages should be consumed within 1 week by closing their mouths.

Storage

It should be stored in its original package, in a cool and dry place protected from frost. In short-term storage, maximum 3 pallets should be placed on top of each other and shipment should be made with the first-in, first-out system. In long-term storage, pallets should not be placed on top of each other.

Safety Precautions

It is dangerous to approach the storage and application areas with fire. Storage and application areas should be ventilated. During the application, work clothes, protective gloves, goggles, masks in accordance with the occupational health and safety rules should be used. During storage and application, it should not be contacted with the skin and eyes, should be washed immediately with plenty of water and soap, and if swallowed, seek medical attention immediately. Food and drink materials should not be brought to the application areas. It should be stored out of the reach of children. For detailed information, please refer to the Material Safety Data Sheet.

Disclaimer

The data contained in this technical document is based on our scientific and practical knowledge. SARTECH Yapı Malzemeleri San. & Tic. Ltd. Sti is only responsible for the quality of the product. Except for the written suggestions about where and how the product will be used and / or results that may occur due to misuse, SARTECH Yapı Malzemeleri San. & Tic. Ltd. Sti. cannot be held responsible. The responsibility for the correct application of our product lies with the user. Our company is only responsible for the quality of the product. This catalogue invalidates the information in the previous catalogue. Our company has the right to make changes in all kinds of information and content details in this catalogue. It is essential to check that the information in the catalogue is current and valid. All rights reserved.