

INNO-FEES FOX BETON RP25

Ready Dry Concrete/Screed Mortar

Description

FOX BETON RP25 is a cement-based, ready-mixed dry concrete/screed mortar with polymer additives, fiber reinforced, with C25 concrete strength.

Fields of Application

- Interiors and exteriors,
- Correcting surface defects and eliminating level differences,
- Where smooth, polished finish is desired,
- On door and window lintels, beams and lintels,
- Used in flooring and in many areas.

Advantages

- Easy application,
- Saves time and labor,
- It prevents crack formation thanks to the additives it contains.
- Thanks to its homogeneous mixture, it provides the same and high strength at every point of the application.
- Since it is a ready mix, material wastage is at minimum level.

Technical Features

Structure of the Material	Cement based, polymer and fiber reinforced
Fresh Mortar Density	2,00 kg/m ³
Color	Grey
Compressive Strength	≥25 N/mm ²
Tensile Strength	≥6 N/mm ²
Particle Size	0-4 mm
Fire Resistance	A1fl
Application Thickness	10 mm-100 mm

The above values are given at +23°C and 50% relative humidity. High temperatures shorten the time, low temperatures increase the time.

Application Procedure

Substrate Preparation

The substrate must be clean, dry, dust-free, sound, not frozen, salt/lime vomited. If there is cement, plaster, plaster etc. on the floor, the floor should be cleaned. Weak concrete pieces should be removed from the surface, small gaps and holes should be made completely open. The resulting dust should be cleaned with the help of industrial vacuum cleaner. In applications to be made on concrete and existing screed, it is important to prime the surface with a specially prepared primer with **FOX BINDER FM125** to increase adhesion.

Primer

In order to increase the adherence in **FOX BETON RP25** application, the surface should be primed with the wet-to-wet application method. Mixture is prepared for priming by adding 2 units of water to 1 unit of cement and 1 unit of **FOX BINDER FM125**. The mixture, which is brought to a consistency that can be applied with a brush, is spread homogeneously with a consumption of **0,35 kg/m²** on the moistened floor that has been cleaned 12 hours beforehand. **FOX BETON RP25** should be applied on the primer before allowing it to dry.

Mixing Ratio

For Mortar Consistency:

For 1 kg of **FOX BETON RP25** approximately 85-90 ml of water should be used.

For 25 kg/bag of **FOX BETON RP25** approximately 2,125-2,25 liter of water should be used.



For Dry Screed Consistency:

For 1 kg of FOX **BETON RP25** approximately 70-80 ml of water should be used.

For 25 kg/bag of **FOX BETON RP25** approximately 1,75-2,0 liter of water should be used.

Application

Surface Correction, Screed Application

FOX BETON RP25 should be mixed with a concrete mixer or hand mixer for 4-5 minutes until it becomes homogeneous. It is spread and corrected with the help of a trowel or other necessary hand tools. Premature drying of the mortar should be prevented. It should dry under natural conditions. There is a risk of cracking and not reaching the desired strength conditions of the mortar, which is dried by making drafts or by being forced to dry by external factors. Depending on the weather conditions, the product can be polished on the surface with the help of tray polishing after approximately 1.5-2 hours. If the outdoor conditions are very challenging for 1 week from the day the product is applied, it should be covered or wetted.

Coverage

For 1 cm application: 20 kg/m²

Watch Points

- In the application of **FOX BETON RP25**, if the ambient and surface temperature is below +5°C or above +25°C, appropriate temperatures should be awaited.
- The applied fresh product should be protected from sunlight and wind so that it does not dry quickly.
- Do not apply in extremely hot, rainy or windy weather. The materials to be used in the application area should be brought and stored 1-2 days in advance and it should be ensured that they adapt to the ambient conditions.
- In applications to be made in extremely cold weather, the ambient and floor temperature should be increased with heaters, and the materials to be used should be conditioned at +20°C - +25°C and made ready for application.
- Working and reaction times of cement-based systems are affected by ambient and ground temperature and relative humidity in the air. The reaction slows down at low temperatures, which extends pan (pot) life and working time. High temperatures accelerate the reaction and the times mentioned above are shortened accordingly.
- In order for the material to complete its cure, the ambient and ground temperature must not fall below the minimum allowable temperature.
- If the mixing water amounts specified in the technical document are exceeded, the product will experience a loss of strength.

Package

25 kg kraft bag

Shelf Life

Shelf life is 12 months from the date of production when properly stored at room temperature, away from direct sunlight between +5°C and +30°C.

Storage

It should be stored in its unopened original package, in a cool and dry environment, away from direct sunlight and protected from frost. In short-term storage, shipment should be made with a first-in, first-out system. In long-term storage, pallets should not be placed on top of each other.

Safety Precautions

It is dangerous to approach the storage and application areas with fire. Storage and application areas should be ventilated.

During the application, work clothes, protective gloves, goggles, masks in accordance with the occupational health and safety rules should be used. During storage and application, the material should not be contacted with the skin and eyes, if contacted, should be washed immediately with plenty of water and soap, and if swallowed, should be sought medical attention immediately. Foods and drinks should not be taken into the application areas. The material should be stored out of the reach of children.

For detailed information, please refer to the Material Safety Data Sheet.



Disclaimer

The data contained in this technical document is based on our scientific and practical knowledge. SARTECH Yapı Malzemeleri San. ve Tic. Ltd Şti. is only responsible for the quality of the product. From the results that may occur due to misuse and other than written suggestions about where and how to use the product, SARTECH Yapı Malzemeleri San. ve Tic. Ltd Şti. cannot be held responsible. The responsibility of the correct application of our product belongs to the user. Our company is only responsible for the quality of the product. This technical form is valid only till a new version is implemented and nullifies the old ones. Our company has the right to make changes in all kinds of information and content details in this catalog. It is imperative to check that the information in the catalog is current and valid. All rights reserved.

