

INNO-PAINT FOX DECODUR M 1.0 / M 1.5 / M 2.0 / M 3.0 / M 4.0

Acrylic Based Decorative Plaster

Description

FOX DECODUR M, is a silicone, acrylic, copolymer emulsion based, self-cleaning, photocatalytic, UV resistant, ready to use, first class exterior or interior wall coating with texture.

It meets the requirements of TS 7847 standard /G₃-E₅-S₄-V₂-W₃.

Usage Areas

- On the interior and exterior of all buildings,
- On all kinds of concrete screed, plaster, screed and cement-based surfaces,
- On exterior thermal insulation systems,
- On old surfaces (consult us for problem and solution suggestions)
- On surfaces with aerated concrete plaster applied,

Advantages

- It has high water vapor permeability.
- It has ideal application time.
- It has water repellent feature.
- Ready to use.
- It provides crack control and is impact resistant.
- It can be colored with all the color tones of the **Fox Bau** system.

Technical Data

Structure of Material		Arcylic, Mineral fillers, Polymer additives
Density		1,70-1,90 g/cm ³
Color		White, Colored
Adhesion Strength	28 days	>1 N/mm ²
Gloss	EN ISO 2813	G ₃
Dry Film Thickness	EN 1062-1	E ₅
Grain Size	EN ISO 787-7	S ₄
Water Vapor Transfer Rate	EN ISO 7783-2	V ₂
Water Transfer Rate	EN 1062-3	W ₃ (≤0,05 kg/(m ² h ^{0,5}))
Application Surface Temperature		+5°C / + 30°C
Ripening Time		3-5 minutes
Usage Time		1 hour
Resistance to Fire	EN 13501-1	A2-s1,d1

The above values are given at +23°C and 50% relative humidity. High temperatures shorten the time, low temperatures lengthen the time.



Application Procedure

Surface Preparation

For cement-based surfaces, the surfaces to be applied must be sound, free from all kinds of dust and dirt, and in balance. Dusting, crumbling mineral-based surfaces, surfaces exposed to windy and hot weather, cement-based surfaces should be strengthened by using **FOX DECODUR PRIMER** as a decorative plaster primer before application.

Mixing

Before the application, the material should be mixed thoroughly until it becomes homogeneous.

Application

20 m² areas should be determined with paper tapes so that there are no joints on large surfaces and color transitions can be harmonious. **FOX DECODUR M** should be mixed thoroughly until it becomes homogeneous. **FOX DECODUR M** should be spread evenly on the surface with a stainless steel trowel on the cured plaster. The surface can be patterned with a circular motion with a stainless steel trowel. Before **FOX DECODUR M** hardens, the adhesive tapes must be carefully removed.

Cleaning of Tools

All tools and equipment used after the application should be cleaned with water before drying.



Coverage

TYPE	APPROXIMATE COVERAGE
M 1.0	1,80 kg/m ²
M 1.5	2,30 kg/m ²
M 2.0	2,50-3,00 kg/m ²
M 3.0	4,30 kg/m ²
M 4.0	5,00 kg/m ²

The coverages amount given is average values. The amount of coverages may vary according to the weather conditions, the application surface and the absorbency of the surface.

Watch Points

- In **FOX DECODUR M** application, if the ambient and surface temperature is below +5°C or above +30°C, suitable temperatures should be expected. It should not be applied in extremely hot, rainy and very windy weather.
- It should be protected from sun, rain, wind and frost for the first 24 hours in outdoor applications.
- High temperatures accelerate hydration and the working time is shortened accordingly. Low temperatures slow down hydration, which prolongs working time. In order for the material to complete its curing, the floor temperature and ambient temperature to be applied must not fall below the minimum allowable temperature.

Package

25 kg bucket

Shelf Life

Shelf life is 12 months from the date of production when properly stored at room temperature, away from direct sunlight between +5°C and +30°C. Opened packages should be closed and consumed within 1 week.

Storage

It should be stored in its unopened original package, in a cool and dry environment, protected from frost.

Safety Precautions

It is dangerous to approach storage and application areas with fire. Storage and application areas should be ventilated. During the application, work clothes, protective gloves, glasses and masks in accordance with the occupational and worker health rules should be used. During storage and application, it should not be contacted with the skin and eyes, in case of contact, it should be washed with plenty of soap and water. If swallowed, a doctor should be consulted immediately. Food and beverage materials should not be brought into the application areas. It should be stored out of the reach of children. For detailed information, the Material Safety Data Sheet should be consulted.

Disclaimer

The data contained in this technical document is based on our scientific and practical knowledge. SARTECH Yapi Malzemeleri San. ve Tic. Ltd. Sti. only responsible for the quality of the product. SARTECH Yapi Malzemeleri San. ve Tic. Ltd. Sti. cannot be held responsible. The responsibility for the correct application of our product belongs to the user. Our company is only responsible for the quality of the product. This catalog overrides the information in the previous catalogue. Our company reserves the right to make changes in any information and content details in this catalogue. It is essential to check that the information in the catalog is up-to-date and valid. All rights reserved.

