

## INNO-FLOOR FOX HARDTOP® LI GLOSS FF847

**Lithium Silicate Based, Silicone and Polymer Modified, Stain and Abrasion Resistant, High Gloss, Concrete Sealer**

### Description

**FOX HARDTOP® LI GLOSS FF847** is a lithium silicate based, silicone and polymer modified, high-gloss concrete sealer material that provides stain and abrasion resistance.

### Fields of Application

- Shopping malls,
- Supermarkets,
- Car parks,
- Airport Hangars,
- Depots,
- Distribution centres,
- Production facilities,
- Schools and Universities,
- Hospitals and pharmaceutical industry,
- Offices,
- Factories,

### Advantages

- High Lithium content
- 100% active substance of solid substance
- Has the feature of fast polishing and stain resistance.
- Can be applied on old and new concrete.
- Excellent penetration.
- Increases abrasion resistance by 20-50%.
- Resistant to stain and water.
- Very fast application feature
- Environmentally friendly, in compliance with the LEED and BREEAM standards.

### Technical Features

Density	1,10 gr/cm <sup>3</sup>
Colour	White
pH	11,30
Solids by %	%18
Active substance percentage	%100
Dilution	No dilution
Application Surface Temperature	+5°C / +35°C

The above values are given for + 23°C and 50% relative humidity. High temperatures shorten the time, low temperatures extend the time.

### Surface Quality

The sub-surfaces to be applied must be strong, clean, dry and free from all kinds of dirt, oil, grease, coating and surface curing materials etc. Ground temperature should be +5°C and above.

### Application Procedure

#### Substrate Preparation

The sub-surfaces to be applied must be strong, clean, dry and free from all kinds of dirt, oil, grease, coating and surface curing materials etc.



## Application Conditions

- The application surface, material and ambient temperature should be between + 5°C and 35°C.
- Temperature must be above 5°C for at least 4 hours after application.
- In hot conditions, it may be necessary to spray water on hot concrete to cool the surface before application.
- Avoid contact with metal, glass, wood, paint or brick. If these surfaces are accidentally exposed to application, the surface should be washed immediately with clean water.

## Mixing

**FOX HARDTOP® LI GLOSS FF847** is a one component, ready to use material.

## Application

**FOX HARDTOP® LI GLOSS FF847** can be applied on newly poured concrete surfaces, no preparation is required. Remove all dirt, deposits and deposits from the existing concrete surface. Let the cleaned surfaces dry. Prepare the surface with polishing and finishing machines and diamond discs or cleaning and maintenance pads. Apply **FOX HARDTOP® LI STANDARD FF840 / FOX HARDTOP® LI PREMIUM FF845** up to 100-400 grids, then apply **FOX HARDTOP® LI GLOSS FF847** with a soft / white polish pad or microfiber mop. Make sure that the application is made on the whole surface without any gaps.

Spread **FOX HARDTOP® LI GLOSS FF847** with a pre-moistened polishing pad (mop). Reapply in areas which dries before 10 minutes.

Wait for the applied surfaces to dry completely. Continue polishing **FOX HARDTOP® LI STANDARD FF840 / FOX HARDTOP® LI PREMIUM FF845** with 800-3000 grits resin pads depending on the desired gloss level on the existing concrete surface. Polish with Shine Pro Buff. The surface is ready to use when it is dry, but the reaction can take up to two weeks to complete depending on temperature and weather conditions.

## Cleaning of the Tools

After the application, the tools and equipment used should be cleaned with solvent or polyurethane thinner. **FOX HARDTOP® LI GLOSS FF847** can only be removed from the surface by mechanical methods after hardening.

## Coverage

Approximately 20-30 gr/m<sup>2</sup> (2 layers)

## Watch Points

- The materials to be used must be brought to the application site 1-2 days prior and must adapt to the ambient conditions.
- Rain, dust, wind, animals and pests should be prevented from entering the building while the coating is fresh.
- After the application is completed, the coating should be protected from direct water contact for at least 72 hours. If water contact occurs, there will be softening and blistering on the coating, which will cause the coating to lose its properties. Therefore, the coating should be completely removed and rebuilt.
- Consumptions are given for ideal conditions where ambient and surface temperatures are considered as 20°C. Actual consumption may vary depending on the surface structure and ambient temperature. It should be remembered that consumption will increase in bad surfaces and cold weather conditions.

## Package

30 kg/bin

## Shelf Life

When stored properly at room temperature, away from direct sunlight, between +5°C and +35°C, its shelf life is 12 months from the date of manufacture.

## Storage

It should be stored in its original package, in a cool and dry place, away from direct sunlight and protected from frost. For short term storage, maximum 2 pallets should be placed on top of each other and shipment should be made with the first in, first out basis. In long-term storage, pallets should not be placed on top of each other.





## Product Technical Data Sheet

Revision Date : 03.01.2019

Revision No : 0

### Safety Precautions

It is dangerous to approach the storage and application areas with fire. Storage and application areas should be ventilated. During the application, work clothes, protective gloves, goggles, masks in accordance with the occupational health and safety rules should be used. During storage and application, it should not be contacted with the skin and eyes, should be washed immediately with plenty of water and soap, and if swallowed, seek medical attention immediately. Food and drink materials should not be brought to the application areas. It should be stored out of the reach of children.

For detailed information, please refer to the Material Safety Data Sheet.

### Disclaimer

The data contained in this technical document is based on our scientific and practical knowledge. SARTECH Yapı Malzemeleri San. & Tic. Ltd. Sti is only responsible for the quality of the product. Except for the written suggestions about where and how the product will be used and / or results that may occur due to misuse, SARTECH Yapı Malzemeleri San. & Tic. Ltd. Sti. cannot be held responsible. The responsibility for the correct application of our product lies with the user. Our company is only responsible for the quality of the product. This catalogue invalidates the information in the previous catalogue. Our company has the right to make changes in all kinds of information and content details in this catalogue. It is essential to check that the information in the catalogue is current and valid. All rights reserved.



**Merkez/Fabrika**  
Organize Sanayi Bölgesi 1. Kısım  
7. Cadde No:6 Döşemealtı/Antalya-TÜRKİYE  
Tel.: +90 (242) 221 42 50 • Faks : +90 (242) 221 42 55