

## INNO-FLOOR FOX SSL® 810 RAPID

**Cement and Synthetic Dispersion Polymer Based, One Component, High Performance Self Leveling Floor Leveling Screed that can be walkable after 3 hours**

### Description

**FOX SSL® 810 RAPID** Cement and Synthetic Polymer Based, one component, high performance, sandpaperable, self-leveling floor leveling screed that can be applied up to 1-10 mm thickness, walkable after 3 hours.

**It meets the requirements of EN 13813:2002 standard CT-C25-F5.**

CT : Cement Based

C25 :  $\geq 25$  N/mm<sup>2</sup> Compression Strength

F5 :  $\geq 5$  N/mm<sup>2</sup> Flexural Strength

### Fields of Application

- In hospitals,
- In stores,
- In school and administrative buildings,
- In hotels,
- In apartments,
- In supermarkets,
- In shopping centers,
- For leveling and removing defects of rough and rough concrete surfaces,
- For leveling rough surface screeds before bonding ceramic, marble, natural stone, parquet, carpet and PVC coatings.

### Advantages

- It can be applied with a pump.
- Has a smooth and perfectly finished surface texture
- Provides fast and easy application.
- Does not shrink, does not dust.
- It spreads by itself and comes to the balance.
- It is economical.
- It is mixed only with water.

### Technical Data

Structure of Material				Mineral fillers and special polymer fillers	
Color				Grey	
Dry Density				1,30±0,05 kg/Lt	
Fresh Mortar Density				2,10±0,05 kg/Lt	
Compressive Strength	EN 13892-2	28 days	$\geq 27,5$ N/mm <sup>2</sup>		
Compressive Strength	EN 13892-2	7 days	$\geq 16,5$ N/mm <sup>2</sup>		
Compressive Strength	EN 13892-2	3 days	$\geq 8,5$ N/mm <sup>2</sup>		
Flexural Strength	EN 13892-2	28 days	$\geq 6,65$ N/mm <sup>2</sup>		
Flexural Strength	EN 13892-2	7 days	$\geq 3,00$ N/mm <sup>2</sup>		
Flexural Strength	EN 13892-2	3 days	$\geq 2,70$ N/mm <sup>2</sup>		
Breaking Strength	EN 12190	28 days	$\geq 2$ N/mm <sup>2</sup>		
Application Surface Temperature					+8°C /+30°C
Spread					25±1 cm
Usage Time					~20 min.
Application Thickness				1-10 mm	
Walkable Time				2-3 hours	
Coating Time on it				24 hours *	

The above values are given at +23°C and 50% relative humidity. High temperatures shorten the time, low temperatures lengthen the time.

\*The coating time on 5 mm and above thicknesses is between 36-48 hours.



## Substrate Quality

Concrete substrates on which the application will be made must be strong and have sufficient compressive strength (minimum 25 N/mm<sup>2</sup>), tensile strength must be at least 1.5 N/mm<sup>2</sup>, humidity ratio must be maximum 4%, ground temperature must be minimum +8°C. In addition, care should be taken to ensure that the dew point of the floor is above +3°C. The substrate must be clean, dry and free from any foreign matter such as dirt, oil, grease, coating and surface curing materials.

## Application Procedure

### Surface preparation

Concrete substrates on which the application will be made should be prepared using abrasive equipment (Shot Blasting, milling cutter, diamond grinding, etc.) to remove the cement grout and obtain an open porous surface. Weak concrete pieces should be removed from the surface, small gaps and holes should be made completely open. The resulting dust should be cleaned with the help of industrial vacuum cleaner.

### Mixing

Pour the amount of water indicated on the packaging into a clean mixing bowl. Add **FOX SSL® 810 RAPID** slowly into the water and mix for 3-4 minutes until you get a homogeneous mixture with an electric mixer and a suitable mixing tip. The material should not be allowed to clump at the bottom of the bucket and these lumps should be dispersed. After waiting for about 2 minutes, mix for 1 more minute and make it ready for use.

### Mixing Ratios

For 25 kg / 1 bag of **FOX SSL® 810 RAPID**, approximately 5,00±0,25 lt of water should be used.  
Approximately 200±10 ml of water should be used for 1 kg of **FOX SSL® 810 RAPID**.

## Application

### Primer

The floor should be primed in order to increase the adherence of **FOX SSL® 810 RAPID** leveling screed to the floor, to reduce the air bubbles that will form and to prevent the mixing liquid from being absorbed by the floor. In the selection of primer, the surface properties should be examined and the time requirement should be calculated. **FOX PRIMERA® FL220** or **FOX UNIPRIMER FL555** primer, selected according to needs, is mixed with water at a ratio of 1/1 and applied with a brush or roller. 2nd layer is applied on very absorbent surfaces. After the primer has dried, **FOX SSL® 810 RAPID** application can be started.

### Coating

**FOX SSL® 810 RAPID** is poured onto the surface and applied at the desired thickness with a comb or a suitable trowel. When the coating reaches the appropriate consistency, a spiked roller should be applied and its air should be removed. Hedgehog roller traces may remain on the surface in case of being late for the spiked roller application.

### Cleaning of Tools

Tools and equipment used after the application should be cleaned with water. **FOX SSL® 810 RAPID** can only be mechanically removed from the surface after hardening.

### Consumption

To obtain 1 mm thickness, 1.7 kg/m<sup>2</sup> **FOX SSL® 810 RAPID** mixture should be used.

### Watch Points

- In the application of **FOX SSL® 810 RAPID**, if the ambient and surface temperature is below +8°C or above +30°C, suitable temperatures should be expected.
- Do not apply in extremely hot, rainy or windy weather.
- The materials to be used in the application area should be brought and stored 1-2 days in advance and it should be ensured that they adapt to the ambient conditions.
- In applications to be made in extremely cold weather, the ambient and floor temperature should be increased with heaters, and the materials to be used should be conditioned at +20°C /+25°C to make them ready for application.
- Working and reaction times of cement-based systems are affected by ambient and ground temperature and relative humidity in the air. The reaction slows down at low temperatures, which extends pan (pot) life and working time. High temperatures accelerate the reaction and the times mentioned above are shortened accordingly.
- In order for the material to complete its curing, the ambient and ground temperature must not fall below the minimum allowable temperature. After mixing, the material should be rested and then mixed again. After applying **FOX SSL® 810 RAPID**, wait at least 3 days before applying another coating.

### Package

25 kg Kraft bag



### Shelf life

It is 9 months from the date of production under suitable storage conditions. Opened packages should be closed and consumed within 1 week. Opened packages should be kept tightly closed and stored under appropriate storage conditions.

### Storage

It should be stored in its unopened original package, in a cool and dry environment, protected from frost. For short-term storage, maximum 2 pallets should be placed on top of each other and the shipment should be made on a first-in, first-out basis. In long-term storage, pallets should not be placed on top of each other.

### Security precautions

It is dangerous to approach storage and application areas with fire. Storage and application areas should be ventilated. During the application, work clothes, protective gloves, glasses and masks in accordance with the occupational and worker health rules should be used. During storage and application, it should not be contacted with the skin and eyes, in case of contact, it should be washed with plenty of water and soap, and if swallowed, a doctor should be consulted immediately. Food and beverage materials should not be brought into the application areas. It should be stored out of the reach of children. For detailed information, the Material Safety Data Sheet should be consulted.

### Disclaimer

The data contained in this technical document is based on our scientific and practical knowledge. SARTECH Yapı Malzemeleri San. ve Tic. Ltd. Şti. is only responsible for the quality of the product. SARTECH Yapı Malzemeleri San. ve Tic. Ltd. Şti. cannot be held responsible for the consequences that may occur due to misuse and/or other than the written recommendations on where and how to use the product. The responsibility for the correct application of our product lies with the user. Our company is only responsible for the quality of the product. This catalog overrides the information in the previous catalogue. Our company reserves the right to make changes in any information and content details in this catalogue. It is essential to check that the information in the catalog is up-to-date and valid. All rights reserved.

