

INNO-DECO FOX STONECARPET® AGREGA

Natural Colored Aggregate

Description

FOX STONECARPET® AGREGA, is a filler material obtained by tumbling or crushing specially selected natural colored aggregates.

Fields of Application

- Used as a filler material in the **FOX STONECARPET®** system
- Suitable for use in:
 - Indoor and outdoor areas
 - Airports
 - Hospitals
 - Galleries
 - Shopping centers
 - Stores and showrooms
 - Hotels

Advantages

- Provides an aesthetic appearance to the surface
- Creates different visual effects when used in various sizes

Color and Size Specifications

2-4 mm Quartz Aggregate	Application Thickness	8 mm
	Colour	Basalt, Dark Grey, Marbled Grey, White, Dark Green, Brown-Burgundy, Brick Red, Pink, Yellow, Cream
2-4 mm Tumbled Aggregate	Application Thickness	8 mm
	Colour	Black, Dark Grey, Grey, White, Yellow, Natural River, Brown-Burgundy, Brick Pink
4-7 mm Quartz Aggregate	Application Thickness	Min. 15 mm
	Colour	Basalt, Dark Grey, Marbled Grey, White, Dark Green, Brown-Burgundy, Brick Red, Pink, Yellow, Cream
4-7 mm Tumbled Aggregate	Application Thickness	Min. 15 mm
	Colour	Black, Dark Grey, Grey, White, Yellow, Natural River, Brown-Burgundy, Brick Pink

Application Procedure

Mix component A of **FOX STONECARPET® BINDER** with a suitable mixer for 1 minute without entraining air. Then pour component B into component A. Continue mixing for 2 minutes until a homogeneous mixture is obtained. After mixing components A and B, add **FOX STONECARPET® AGGREGATE**. Mix for another 2-3 minutes until a homogeneous mixture is achieved. Avoid overmixing to minimize air entrainment.

Application with Trowel

Pour the **FOX STONECARPET® BINDER** – aggregate mixture onto the surface and spread it to the desired thickness using a suitable trowel or screed.

Application with Power Float Machine

Pour the **FOX STONECARPET® BINDER** – aggregate mixture onto the surface. When the surface reaches a consistency that can support the weight of the power float (or when the footprint depth is about 0.5 cm), start finishing with the float machine using a pan to obtain a continuous and smooth surface.

Consumption

For 2-4 mm thickness:

Wall applications: ~10-12 kg/m²

Floor applications: ~15 kg/m²

For 4-7 mm thickness:

~20 kg/m² (per 1 cm thickness)

Package

25 kg



www.foxbau.com

FOX BAU YAPI KİMYASALLARI ANONİM ŞİRKETİ

Merkez : Organize Sanayi Bölgesi 1. Kısım 7. Cadde No:6 Döşemealtı-ANTALYA/TÜRKİYE
Telefon : 0(242) 221 42 50 Fax : 0(242) 221 42 55
Şube 1 : Kargalı Hanbabaosb Mah. Organize San. 10. Sk. No:6 Hendek-Sakarya/TÜRKİYE
Şube 2 : Oyali OSB Mahallesi 3. Cadde No:21 Eğil-Diyarbakır/TÜRKİYE
Web : www.foxbau.com E-mail : info@foxbau.com

Storage

It should be stored in its unopened original packaging, in a cool and dry environment, protected from frost. For short-term storage, maximum 3 pallets should be stacked on top of each other and shipment should be made on a first-in, first-out basis. For long term storage, pallets should not be stacked on top of each other.

Safety Precautions

It is dangerous to approach the storage and application areas with fire. Storage and application areas should be ventilated. During the application, work clothes, protective gloves, goggles, masks in accordance with the occupational health and safety rules should be used. During storage and application, it should not be contacted with the skin and eyes, should be washed immediately with plenty of water and soap, and if swallowed, seek medical attention immediately. Food and drink materials should not be brought to the application areas. It should be stored out of the reach of children.

For detailed information, please refer to the Material Safety Data Sheet.

Disclaimer

The data contained in this technical document is based on our scientific and practical knowledge. Fox Bau Yapı Kimyasalları A.Ş. is only responsible for the quality of the product. Our company cannot be held responsible for the consequences that may occur due to misuse and/or other than the written suggestions about where and how the product will be used. For detailed information, the safety data sheet and technical data sheet should be consulted or our company officials should be contacted.



www.foxbau.com

FOX BAU YAPI KİMYASALLARI ANONİM ŞİRKETİ

Merkez : Organize Sanayi Bölgesi 1. Kısım 7. Cadde No:6 Döşemealtı-ANTALYA/TÜRKİYE
Telefon : 0(242) 221 42 50 Fax: 0(242) 221 42 55
Şube 1 : Kargalı Hanbabaosb Mah. Organize San. 10. Sk. No:6 Hendek-Sakarya/TÜRKİYE
Şube 2 : Oyali OSB Mahallesi 3. Cadde No:21 Eğil-Diyarbakır/TÜRKİYE
Web : www.foxbau.com E-mail : info@foxbau.com