

# INNO-FLOOR FOX PURATHANE® STONE CARPET AGREGA

## Specially Selected Natural Colorful Aggregate

### Description

**FOX PURATHANE® STONE CARPET AGREGA** is filling material obtained as a result of tumbling or breakage of specially selected natural colored aggregates.

### Field of Application

- As a filling material on **FOX PURATHANE® STONE CARPET** system;
- Indoors and outdoors,
- On airports,
- In hospitals,
- In galleries,
- In shopping Malls,
- In super markets,
- In stores and showrooms,
- Used in hotels.

### Technical Features

Minimum Application Thickness of 1-2 mm Quartz Aggregate	6 mm
Color	White, Bottle Green, Variegated Grey, Cream, Bright Green, Maroon Brick Red, Brick Red, Pink, Straw Yellow, Dark Yellow, Black-Bazalt, Sand Beige
Minimum Application Thickness of 1-3 mm Quartz Aggregate	6 mm
Color	White, Bottle Green, Veriaggated Grey, Cream, Maroon Brick Red, Brick Red, Pink, Straw Yellow, Black-Bazalt, Sand Beige
Minimum Application Thickness of 2-4 mm Quartz Aggregate	8 mm
Color	White, Bottle Green, Variegated Grey, Cream, Maroon Brick Red, Brick Red, Pink, Straw Yellow, Black-Bazalt, Sand Beige
Minimum Application Thickness of 2-4 mm Natural Aggregate	8 mm
Color	Tile(Pink), Grey, Yellow, White, Maroon, Black, River Bottom, Sand Beige

### Quality of Substrate

The concrete substrates on which the product is going to be applied should be durable and have compressive strength tensile strength (min. 25 N/mm<sup>2</sup>), the tensile strength of the substrate should exceed 1, 5 N/mm<sup>2</sup>, residual moisture content of the substrate should not exceed 4 %. The substrate temperature should remain +8°C minimum and the temperature of the substrate should at least be 3°C above the current dew point. The substrate must be clean, dry and all kinds of dirt, oil, grease, coating and surface curing materials and so on. should be removed from surface.

### Application Procedure

#### Preparation of Substrate

The concrete substrates on which the product is going to be applied should be prepared to achieve a porous surface by lifting the cement slurry and using abrasive equipment (shot blasting, milling cutter etc.). Weak concrete pieces should be removed from the surface, small gaps, holes should be fully opened. The resulting dust should be cleaned with the help of an industrial vacuum cleaner. The ground must be prepared to repair the substrate, fill the gaps and fix the surface with **FOX SSL®** series levelling screed.



## Package

25 kg Bag

## Storage

The product should be stored in its original package. For short term storage, maximum 2 palettes should be placed on top of each other and the shipment should be made on a 'first come, first go' basis. Palettes should not be placed on top of each other during long term storage.

## Health and Safety Precautions

It is dangerous to approach the application sites with fire. Fresh air should be circulated in the storage and the application sites. During the application, a protective apparel, protective gloves, goggles and masks which comply with the Occupational Health and Safety Rules should be used. Due to the irritation effect of the uncured materials, the mixture should not come into contact with skin and eyes; in case of a contact, the affected area should be washed with plenty of water and soap; in case of swallowing, a physician should be consulted immediately. No food or beverages should be brought to the application area. The product should be stored and kept out of reach of children.

For detailed information please consult the Material Safety Data Sheet.

## Disclaimer

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. SARTECH Yapı Malzemeleri San. Tic. Ltd Şti. is only responsible for the quality of the product. SARTECH Yapı Malzemeleri San. Tic. Ltd Şti. is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.